

LEYCO® -DRAIN

ONE-COMPONENT JOINT FILLER

Description

LEYCO-DRAIN is a ready mixed, vacuum-packed, 1-component pavement fixing mortar.

LEYCO-DRAIN can be used for terraces, garden paths and even occasional car traffic in private driveways.

The surfaces remain water-permeable.

Application

1. Pre-wet the surface. Make sure that all stones have soaked up water.

Caution: the sub-construction must be water-permeable.

2. Then remove sealed bag from the bucket and cut it open.

3. Pour the contents onto the prepared surface and work the product well, firmly and compactly into the joints with a coarse broom or rubber slider. Use a soft jet of water to rinse the material into the joints.

The minimum depth of joints is 30mm, minimum width is 8mm.

4. After filling the joints completely, clean the surface by brushing diagonally to the joints with a fine brush. Then clean with clear water and rinse remaining oil residues off.

5. The ready surface can be walked on after approx. 24 hours. The final curing will be complete within approx. 7 days.

Note: Test material on inconspicuous sample site before usage! Read Technical Data Sheet before Usage!

Handling:

Dimensioning of joints: Joint width: min 8 mm

Joint depth: min 30 mm

Processing temperature: min +0°C dry weather

In case of a reconstruction area, joint depth is created by blowing or washing out (30mm).

In order to avoid sandbinder residues on absorbent stones, the paving should be pre-wet.

Note: Do not sweep material residues into the open joints.

The surface is ready for use after approx. 24 h for pedestrian use, car use after 7 days under conditions of 20°C, 65% humidity. Lower temperatures lengthen, higher temperatures accelerate the curing time.

Cleaning:

After usage clean all utensils with usual detergents. After hardening employ mechanical cleaners. Workers are recommended to wear protective clothing.

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 29.08.2011

Leycochem-Iraq

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151

Email: sales.leycochem.iraq@leyde.com

www.leyde.com

LeycoChem LEYDE GmbH Germany

Industriestrasse 155

P.O. Box 501627

D-50999 Köln/Cologne

Tel.:+49(0)2236-96600-0

Fax:+49(0)2236-96600-10

Email: leycochem@leyde.com